

GP® TITANFLEX® is a loose laid multilayer, low polyethylene membrane. GP® TITANFLEX® is specifically designed, manufactured and tested and certified to perform as a methane, carbon dioxide, radon, ground gas, VOC air & moisture and hydrocarbon protection system. GP® TITANFLEX® is used as a loose laid membrane for the gas/VOC protection of ground level structures. Features and benefits:

- · Can be a fully welded system.
- · Exceptional chemical resistance.
- Long term durability performance is guaranteed for the lifetime of the building.
- Conform with the latest codes of practice as published by BRE, CIRIA and BSI.
- · High resistance to ground gases.

Part of the GP® TITANTECH® family of membranes, the GP® TITANFLEX® is a high performance, hydrocarbon barrier, manufactured from a unique HDPE resin. The primary membrane has excellent chemical resistance and is ideal for use on sites affected by hydrocarbon and VOC contamination. It will also effectively prevent the ingress of a number of other harmful gases, including radon, methane and carbon dioxide.

Certifications





Please Scan



Rev 2024

Accessory Products

- GP® TITAN Tape
- GP® TITANTECH® DPC
- GP® TITAN Overtape
- · 300TT

Physical Properties

 $\begin{array}{lll} \text{Thickness} & 0.5 \text{ mm} \\ \text{Width} & 2 \text{ m} \\ \text{Length} & 50 \text{ m} \\ \text{Weight} & 500 \text{ g/m}^2 \\ \end{array}$

Gas Permeability

 Methane
 0.13

 Carbon Dioxide
 3.01

 Radon
 1 x 10⁻¹²

Compliance and Certification
CE MARK - EN13967:2012
NHBC Standards Compliant
B58485:2015 +A1 2019 Accordant
CIRIA C748 Accordant
BBA Certified - Certificate No.
18/5581 P1

Specification Clauses

Uniclass 2015 - PR_25_57_65_90 Plastic Sheets


CAWS - J40/145 Loose laid weldable polyethylene gas retardant damp proofing J40/140 loose laid plastics or rubber sheet gas retardant damp

D21/350 Gas retardant membrane




GP® TITANFLEX® Vapour Permeability 100% Concentration			
Benzene	< 3.6 mg /m² / day	Vinyl Chloride	< 0.05 mg /m ² / day
Toulene	< 13.8 mg /m² / day	Trichlorothene (TCE)	< 54.7 mg /m² / day
Ethyl Benzene	< 2.7 mg /m² / day	tetrachlorothene (PCE)	< 26.2 mg /m² / day
Xylenes (M,P,O)	< 7.7 mg /m² / day	Napthalene	< 0.0006 mg /m² / day
Hexane	< 0.6 mg /m² / day	CIS-1,2-Dichloroethylene	< 1.1 mg /m² / day

Standard Detail - Slab / Wall Kicker Joint






Standard Detail - Head of Retaining Wall






Standard Detail - Typical Piled Pit





Standard Detail - Typical RC Pit





Standard Detail - Typical Capping Beam

